



THL International Ltd
Laragh
Castleblayney
Co Monaghan
Tel: 042-9745031 01-6785040 ;
email: sales@thlint.com
www.thlint.com

Instructions for use

Suregrip[®] solvent free epoxy coating

(100% solids, fast cure 2 part floor paint)

Supplied : Base unit 3.75 kg metal tin (Coloured liquid)
Hardener unit 1.25 kg plastic jerrican (Amber liquid)

Thinners : Supplied separately.

Application tools : Large paint tray or paint scuttle.
Double sided roller frame and sleeves (Medium pile); paint brush.
Electric drill with spiral paint mixer. Masking tape.
Protective gloves, eye protection etc, Cloths (to clean)

Suregrip[®] is intended for professional use only.

Suregrip[®] solvent free is a fast reacting floor paint and each unit should be applied within 15 minutes of mixing. Ready for light foot traffic after 7 hours (@ 20°C)

Preparation: Ensure surface is clean and dry . (all oil, grease water removed and dry)
Abrade surface (Shot-blast / sand / diamond grind)
Small holes in floor can be filled with “isopon” or similar prior to painting.
Larger holes and cracks require resin mortar repairs
Any repairs should be left flush with surface.
Use masking tape to protect areas not to be coated

Mixing: Do not start to mix product until ready to apply coating.
Use disposable vinyl gloves, barrier cream and eye protection to protect from resin.
(avoid skin contact, refer to Material safety data sheets)
If mixing by hand, (Not recommended)

Do not use a round stick to mix, use flat paint scraper or similar

Ensure bottom and sides are well mixed and is an even colour without streaks
Pour contents of hardener into the large base unit and mix thoroughly (use drill with paddle)
Ensure bottom and sides are mixed. (Mix for about 1 minute)

Pour mixed product into paint tray and re-mix .
Up to ½ lt of thinners can be added to tin to help clean any residual paint.

Add this to paint tray and mix again. (for about 1 min)

(Thinners are not necessary but help with the rolling of the paint esp. in colder weather or as a primer coat)

Mixing Ratio :: Weight =: 3:1
Volume = 1 litre base : 400ml hardener

(It is not recommended to split tins unless necessary)

Application: Mixed product must be applied within 20 minutes (less if warm)
Apply with rollers to larger areas and use a brush to cut in.
Yield should be from 20 -25m² per pack depending on substrate.

Thinners can be used to clean contaminated surfaces. (with care)

Product should cure for foot traffic in less than 7 hours. (@20°C) Colder temperatures delay cure

Normally rollers, paint brushes etc are disposed of after use.

Full Technical Data sheet and Material safety sheets are available on web site.

Resin coatings have limitations that you should familiarise yourself with.